Intrarea Sulfinei 94 Magurele, Ilfov. Tel: 021 312 56 60, E-mail: office@tehnicaldent.ro IBAN: RO17 RNCB 0068 0043 7192 0001 Nr. Inreg. Reg. Com.: J/09/137/99, Cod fiscal: RO 117 58 273

Rasina printare baza proteze 1L



Pret:

2.478,77 lei TVA inclusa

Descriere produs:

Rasina printare pentru proteze dentare. Acest material are cea mai buna performanta in ceea ce priveste rezistenta la flexiune, duritatea ridicata si vascozitatea scazuta, fara ca produsul sa fie fragil.

Prezinta o buna stabilitate a culorii, fara gust si usor de curatat. Culoare naturala a gingiei si textura excelenta.

Se recomanda depozitarea la temperatura camerei 23±2 cu umiditate 70%

Proprietati fizice (stare lichida)

Culoare: Natural, Roz deschis, Roz deschis rosiatic

Vascozitate (25°C): 750cps

Lungime de unda: 405nm

Proprietati mecanice (dupa polimerizare)

Intrarea Sulfinei 94 Magurele, Ilfov. Tel: 021 312 56 60, E-mail: office@tehnicaldent.ro IBAN: RO17 RNCB 0068 0043 7192 0001 Nr. Inreg. Reg. Com.: J/09/137/99, Cod fiscal: RO 117 58 273

Rezistenta la tractiune: 7%

Modul de flexiune: 2800 MPa

Rezistenta la inconvoiere: 75 MPa

Biocompatibil

Post-procesare

Timp de curatare cu etanol 95%. Curatare manuala: 20 secunde

Timp de polimerizare recomandat Fabcure 2: 10 minute - 60°C

Mechanical Properties - Post Cured Parts

Property	Value	Reference/Standard
Flexural Strength	98 MPa	ISO 178
Flexural modulus	2800 MPa	ISO 178
Flexural Strength	75 MPa	ISO 20795-2
Impact strength	> 2.5 kJ/m2	ISO 180
Elongation at break	7%	ISO 527-1
Biocompatible	Comply	ISO 10993-1

Post Processing	Value
Cleaning time with 95% ethanol	Manual cleaning 20 secs
Recommended curing time	Fabcure 2: 10min at 60 degrees

Prezentare

Flacon 1L